

## TESA 4934

### Technical Data

Backing material	cloth
Colour	white
Thickness of tape	200 µm
Type of adhesive	synthetic rubber
Elongation at break	20 %
Tensile strength	35 N/cm
Type of liner	glassine

### Adhesion to

Steel (initial)	14.5 N/cm
PE (initial)	8 N/cm
PP (initial)	16 N/cm
PVC (initial)	14 N/cm
Steel (after 14 days)	24 N/cm
PE (after 14 days)	8.5 N/cm
PP (after 14 days)	24.5 N/cm
PVC (after 14 days)	22.5 N/cm

### Properties

Temperature resistance short term	60 °C
Temperature resistance long term	40 °C
Tack	++
Humidity resistance	+
Static shear resistance at 23 °C	++
Static shear resistance at 40 °C	++
Static shear resistance at 70 °C	-
Fogging	++
Ageing resistance (UV)	o