

DATA SHEET

DT911 DOUBLE COATED NON WOVEN POLYESTER

Adhesive	:	Acrylic / Solvent base
Tack	:	J. Dow No. 24
Release Liner	:	White Kraft 110g/m ²
Carrier	:	Non Woven Polyester 14g/m ²
Thickness	:	0.12 ± 0.01mm
Peel Adhesion	:	PSTC-3 3.5kgs/ 25mm
Shear Strength	:	PSTC-7 Over 24 Hours at 25°C 1.0kg 25mm x 25mm
Service Temperature	:	-40°C to 40°C

Description

High bonding for use in many industrial applications.

Foam lamination and splicing.

For temporary but instant sailcloth seaming before stitching and splicing of different types of fabrics

Offers excellent resistance to alkalisation.

Date of Issue : May 2009

THE USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE AND THE USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH.