productinformation

tesa® 4967 Double-sided extra strong filmic tape

tesa® 4967 is a transparent double-sided self-adhesive tape consisting of a PET backing and a modified acrylic adhesive.

tesa® 4967 features:

- Extremely high holding power even at elevated temperatures ÷.
- Superior converting performance due to strong PET backing and reduced adhesive mass flow .
- Good bonding performance even to LSE materials

Main Application

- Mounting lenses for mobile phone housings
- Mounting of ABS plastic parts in the automotive industry
- Mounting of decorative profiles and mouldings in the furniture industry

Technical Data

| - | Backing material Color Total thickness | PET film transparent 160 μm | : | Type of adhesive Elongation at break Tensile strength | tackified acrylic 50 % 20 N/cm |
|----|--|-----------------------------------|---|---|--------------------------------------|
| Ac | lhesion to | | | | |

| Steel (initial) | 11.3 N/cm | Steel (after 14 days) 13.4 N/cm | |
|---------------------|-----------|--|--|
| ABS (initial) | 9.8 N/cm | ABS (after 14 days) 10.8 N/cm | |
| Aluminium (initial) | 9.6 N/cm | Aluminium (after 14 days) 12.2 N/cm | |
| PC (initial) | 11.7 N/cm | PC (after 14 days) 13.1 N/cm | |
| PE (initial) | 5.2 N/cm | PE (after 14 days) 5.7 N/cm | |
| PET (initial) | 9.3 N/cm | PET (after 14 days) 10.5 N/cm | |
| PP (initial) | 5.3 N/cm | PP (after 14 days) 7.0 N/cm | |
| PS (initial) | 10.2 N/cm | PS (after 14 days) 11.1 N/cm | |
| PVC (initial) | 8.9 N/cm | PVC (after 14 days) 11.9 N/cm | |
| | | | |

Properties

| | Temperature resistance short term | 200 °C | | Resistance to chemicals | ••• |
|----|---|--------------------|----|---------------------------------|-----|
| | Temperature resistance long term | 100 °C | • | Softener resistance | ••• |
| • | Tack | ••• | | Static shear resistance at 23°C | ••• |
| • | Ageing resistance (UV) | | | Static shear resistance at 40°C | ••• |
| • | Humidity resistance | •••• | | | |
| E٧ | aluation across relevant tesa [®] assortme | nt: •••• very good | •• | ● good ●● medium ● low | |

For latest information on this product please visit http://l.tesa.com/?ip=04967

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



ę

great to work with

tesa[®] 4967 Double-sided extra strong filmic tape

Additional Information

Liner variants: PV0 brown glassine paper (71µm; 82g/m²) PV6 red MOPP-film (80µm; 72g/m²) PV7 transparent PET-film (50µm; 72g/m²) PV16 white MOPP-film (80µm, 72g/m²)

For latest information on this product please visit http://l.tesa.com/?ip=04967

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

