productinformation

tesa® 51007

PET cloth tape for abrasion protection of automotive harnesses

tesa® 51007 is a PET cloth tape with a rubber-based adhesive providing reliable abrasion protection of automotive harnesses. The unwind force is adapted for automatic bundling and allows high processing speeds.

The high adhesion and good flag resistance ensure secure harness bundling. The temperature resistance depends on the insulation material.

Main features:

- Resistant to abrasion
- High initial tack and adhesion
- Optimized for automatic wrapping
- Flag-resistant
- Can withstand environmental influences
- Constant unwind force optimized for automatic application
- Aging-resistant
- Flame-retardant
- Flexible and smooth

Color: Black

Main Application

tesa® 51007 has been specially designed for bundling and wire protection against abrasion. The main application field is the engine compartment of a car, with demanding temperature-related and environmental conditions.

Technical Data

•	Backing material	PET CIOTN	remperature resistance (3000h)	150°C
	Total thickness	320 μm	Abrasion resistance (10mm	Class C (acc. to
	Type of adhesive	rubber based	mandrel)	LV312)
	Adhesion to steel	4.5 N/cm	Abrasion resistance (5mm	Class B (acc. to
	Elongation at break	22 %	mandrel)	LV312)
	Tensile strength	175 N/cm	Flame resistance as composite	Class B (acc. to
	Temperature resistance min.	-40 °C		LV312)
			Unwind force (roll width ≤ 9mm)	6 N/roll (30 m/min)
			Unwind force (roll width > 9mm)	6 N/roll (30 m/min)
			Noise damping (decibel)	Class A (acc. to
				LV312)

Page 1 of 2 - As of 23/11/2018 - er

For latest information on this product please visit http://l.tesa.com/?ip=51007

tesa® 51007

PET cloth tape for abrasion protection of automotive harnesses

Additional Information

Standard widths: 9, 19, 25, 32 mm

Standard lengths: 50 m

Most combinations of width and length are possible

• Further dimensions are available upon request

Standard core diameter: 76 mmApplicable for red ring assembly aid

*On ETFE wires. Other insulation materials to be tested.

Page 2 of 2 - As of 23/11/2018 - el