

Scapa 9152

80°C Coloured Paper Masking Adhesive Tape

DESCRIPTION

Scapa 9152 is a 0.14mm semi crepe paper tape coated with an aggressive solvent based rubber/resin adhesive system, recommended for all general purpose 80°C colour coding and masking applications.

APPLICATIONS

- Automotive after market masking tape with short term oven baking resistance.
- Book and document binding.
- Colour coding identification.
- Harness branch binding tape.
- Temporary binding and wrapping in the automotive industry.
- Suitable for all general purpose 80°C indoor holding, sealing and masking applications.
- Can be used universally for interior fixing, insulating and sealing applications up to 80°C.

PRODUCT BENEFITS

- Clean and easy removal.
- Easy unwind.
- Flexible and conformable.
- Excellent peel adhesion.
- Good shear and holding strength.
- Resistant to chemicals, lacquers and solvents.
- Resistant to oven baking.
- Continuous temperature resistance: +80°C.

TECHNICAL PROPERTIES

| Technical Property | Nominal Value | Unit | Test Method |
|---------------------|---------------|------|-------------|
| Adhesion to Steel | 3.5 | N/cm | AFERA 4001 |
| Elongation at Break | 11 | % | AFERA 4005 |
| Tensile Strength | 32 | N/cm | AFERA 4004 |
| Total Thickness | 0.14 | mm | AFERA 4006 |

STANDARD PRESENTATIONS

- Colours: Black
- Core: 76mm Scapa branded cardboard core
- Packaging: Concertina
- Roll Length: 50 metres
- Roll Width: 6, 9, 12, 15, 19, 25, 30, 38, 50 and 75mm

RECOMMENDATIONS

The rolls should be stored flat on their cut edges in the original packaging. The product must be protected from dust, heat, moisture, direct sunlight and solvent fumes. Storage temperature between +10°C and +30°C.

Under these conditions, the storage life of the tape in a temperate climate will be at least 6 months. Surfaces should be clean, dry and free of dust, grease, oil or other contaminants. Scapa masking tapes are not suitable for outdoor exposure and should not be submitted to prolonged periods of sunlight, as tapes may become difficult to remove.

Clean removal may also vary with surface type, lacquers, primers and paints nature and the temperature of the surface at removal. For best results, remove the tape as soon as possible after applying the paints pulling it slowly at a 90° angle with constant speed