Product datasheet Issue No 2 Issued Jan 2004 DOUBLE-SIDED POLYPROPYLENE FILMIC TAPE MODIFIED ACRYLIC ADHESIVE, LIGHT WEIGHT LINER

TECHNICAL DETAILS		TYPICAL VALUE	UNITS
Thickness, adhesive + carrier Release liner thickness		0.070 0.070	mm mm
180 degree peel adhesion:	Open side Closed side	750 750	N/m N/m
Polyester loop tack:	Open side Closed side	850 850	N/m N/m
Liner release		10	N/m
Tensile strength		2200	N/m
Elongation at break		75	%
Service temperature		-20 to +100	Deg. C.
Recommended application temperature		+5 to +25	Deg. C.
Shear adhesion, 1Kg @ 23 deg. C.		20	Hours
Shelf life		12	Months
Test Methods: BS 7116			

.THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY ALL DATA IS BASED UPON AVERAGE VALUES . THE PURCHASER SHALL BE RESPONSIBLE FOR .DETEMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES